



KLEBROHSTOFF

KLEBROHSTOFF

Produkt	Produkt - Typ	Newport Handelsname	Farbe (Gardener)	Shmelzpunkt (°C)
Kolophonium Harz	Standard - unbehandelt	Nuroz WVW	Gelblich	≥76
		Nuroz X3	<3	≥83
	Nicht-kristallisierend	Nuroz 331	5-10	77-86
		Nuroz 332	2-8	83-93
		Nuroz 333	5-10	92-98
	Hydriert	Nuroz HR80L	0-1	≥78
		Nuroz HA	8	≥76
	Disproportionierte	Nuroz DP	Gelblich	≥75
	Polymerisiert	Nuroz PR-95	<10	90-100
		Nuroz PR-110		100-120
		Nuroz PR-130		120-135
		Nuroz PR-140		135-145
Harz Ester	Glycerol Ester	Nuroz RE85	3-4	83-90
		Nuroz RE85L	1-2	
	Pentaerythritol Ester	Nuroz RE100	3-4	100-105
		Nuroz RE100L	1-2	
		Nuroz RE100SL	0-1	
		Nuroz RE115	3-4	113-117
		Nuroz RE115L	1-2	
	Malein Ester	Nuroz RM105	3-5	100-110
		Nuroz RM105L	1-2	
		Nuroz RM115	3-5	112-118
		Nuroz RM115L	1-2	
		Nuroz RM125	3-5	120-130
		Nuroz RM125L	1-2	
	Flüssig Harz Ester * (Viskositäet in Pascal sek. @25°C)	Nutac 14277	4 max	2-15
		Nutac 14272	6 max	5-20
		Nutac 14270	10 max	20-50
		Nutac 14025	8 max	17 @ 60°C
		Nutac LRE	8 max	30-100
		Nutac MER-L	4 max	2.0-3.5
		Nutac MEHR-L	2 max	4-7
	Polymerisiertes Harz Ester	Nuroz PRE-115	<10	112-118
		Nuroz PRE-125		120-130
		Nuroz PRE-135		130-140
	Glycerol Harz Ester-hydriert	Nuroz HRGE 85	4-6	85-90
		Nuroz HRGE 85L	3-4	85-90
		Nuroz HRGE 85H	4-6	85-90
	Pentaerythritol Harz Ester-hysrier	Nuroz HRPE 100	4-6	92-102
	Wasser-basierende Harz Ester Dispersion	Aquaroz 15309	-	5-10
		Aquaroz 15305		35-45
		Aquaroz 15200		60-70
		Aquaroz 15100		70-80

KLEBROHSTOFF

Produkt	Produkt - Typ	Newport Handelsname	Farbe (Gardener)	Shmelzpunkt (°C)
Harz Ester - "Food Grade"	Glycerol Ester	Nuroz RE85E	8 max	80-88
	Glycerol Ester-hydriert	Nuroz HRGE 85E		78-88
	Polymerisiertes Harz Ester	Nuroz PRE-110E Nuroz PRE-100E		107-115 90-108
Kohlenwasserstoffharz	Aromatisch	H-Rez C9-100	<10	90-100
		H-Rez C9-110	<7	100-110
		H-Rez C9-120		110-120
		H-Rez C9-130		120-130
		H-Rez C9-140		130-140
		H-Rez C9-150		140-150
	Aliphatisch	H-Rez C5-1095	<6	91-97
		H-Rez C5-1102		96-104
	Aromatisch modifiziert	H-Rez -4100	<6	96-105
	Aliphatisch voll durchhydriert	H-Rez C5-25H	0-1	Liquid
		H-Rez C5-100H		96-105
		H-Rez C5-110H		105-112
Terpene Harz	Terpene Phenol	H-Rez C9-100H	0-1	100
		H-Rez C9-125H		125
		H-Rez AMS-100	Water white	95-105
	Polyterpene - fest	Nures TP 100	7 max	90-100
		Nures TP 125		120-130
		Nures TP 135		130-140
		Nures TP 150		145-155
	Polyterpene - flüssig	Nures T105	4 max	100-109
		Nures T115		110-119
		Nures T125		120-129
	Styrol Terpene	Nutac T25	4-6	15-25
		Nutac T15		5-15
Phenol Harz	Alkyl phenol	Nures ST80	3 max	80-89
		Nures ST90		90-99
		Nures ST100		100-109
	Butyl phenol	Nures 2402	-	90-110
	Bromierte Octylphenol	Nures 2529	-	60-70
Kautschuk	Octylphenol	Nures 2056	-	80-90
	Octylphenol	Nures 2045	-	85-95
	Octylphenol	Nures 203	-	90-104
	Polyisobutylene Rubber	Nuprene PIB		
	Polychloroprene Rubber	Nuprene CR		
Silane	SBS Block Copolymer	Nuprene SBS		
	SIS Block Copolymer	Nuprene SIS		
	PVC Copolymer	Nuprene PVC		
	Amino Silanes	NuSilane AMI		
Silane	Alkyl Silanes	NuSilane ALK		
	Epoxly Silanes	NuSilane ES		
	Vinyl Silanes	NuSilane VS		

ANTIOXIDANTIEN

TYP	Newport Produkt	CAS NR
Phenole	Nuvox 245	36443-68-2
	Nuvox 259	35074-77-2
	Nuvox 1010	6683-19-8
	Nuvox 1076	2082-79-3
	Nuvox 1098	23128-74-7
	Nuvox 1135	125643-61-0
	Nuvox 1330	1709-70-2
	Nuvox 1790	40601-76-1
	Nuvox 3114	27676-62-6
	Nuvox DLTDP	123-28-4
	Nuvox DSTDP	693-36-7
	Nuvox 2246	119-47-1
Phosphit	Nufos 168	31570-04-4
	Nufos Pep 8	3806-34-6
	Nufos 626	26741-53-7
	Nufos TNPP	26523-78-4
	Nufos TPP	101-02-0
	Nufos P-EPQ	119345-01-6
Mischungen	Nuvox B225	Nuvox 1010:Nufos 168 (1:1)
	Nuvox B215	Nuvox 1010:Nufos 168 (1:2)
	Nuvox B561	Nuvox 1010:Nufos 168 (1:4)
	Nuvox B900	Nuvox 1076:Nufos 168 (1:4)
	Nuvox B1171	Nuvox 1098:Nufos 168 (1:1)

For prices, samples and specifications, please contact:

Europe and Rest of the World

Newport Industries Limited, Merlin House, 3rd Floor, 20 Belmont Terrace, Chiswick, London, W4 5UG
Tel - + 44(0) 20 8742 0333, Fax - + 44(0) 20 8742 0444, E-mail - sales@newport-industries.com



North America

Nuroz LLC, 5201 Blue Lagoon Drive, 8th Floor, Miami, Florida 33126, United States
Tel - (001) 305 716 4231, Fax - (001) 305 629 3100, E-mail - sales@newport-industries.com



www.rosin.s.eu • www.newport-industries.com

ISO9001 Registered Company, Member of London Chamber of Commerce and Industry, Co - Registered No. 3407212 - Vat No. 723-0128-80

